


Composition

100% Polyamide + PU

Fabric properties

Number of ends (warp)	.	14,00 DR/CM
Number of picks (weft)	.	12,00 DR/CM
Usable width	.	150,0 CM
Full width	Full width	155,0 CM
Weight with a deviation of 5%	EN 12127 meth 5	384 G/M ²

Mechanical properties

Shrinkage wash 40°C warp	ISO 5077 2007	<3 %
Shrinkage wash 40°C weft	ISO 5077 2007	<3 %
Tensile strength warp	ISO13934-1 2013	3200 N
Tensile strength weft	ISO13934-1 2013	3000 N
Tear strength (3 legs)warp	ISO4674 1A 2003	300 N
Tear strength (3 legs) weft	ISO4674 1A 2003	300 N
Seam slippage warp 80 N	ISO13936-2 2004	0,5 MM
Seam slippage warp 120 N	ISO13936-2 2004	1,0 MM
Seam slippage weft 80 N	ISO13936-2 2004	0,5 MM
Seam slippage weft 120 N	ISO13936-2 2004	1,0 MM
Abrasion 12kPa	ISO12947-2 1998	>100000 CYCLI
Watercolumn	EN20811/ISO811	5000 MM

Colourfastness

		Light	Middle	Dark	Change
Colourfastness to washing 40°C	ISO105C06 2010	5	4/5	4	4
Colourfastness to dry cleaning	ISO105D01 2010	5	4/5	4	4
Colourfastness to water	ISO105E01 2013	5	4	3/4	4
Colourfastness to rubbing dry	ISO105X12 2016	5	4	3/4	
Colourfastness to rubbing wet	ISO105X12 2016	5	4	3	
Colourfastness to light	ISO105B02 2014	5	5	5	

Washing symbols

Special tests

Remark 1	-	ANTIBACTERIAL + ANTIFUNGI
Remark 2	-	ISO 13934-1 TOLERANCE +/-10%
Remark 3	-	ISO 4674-1A TOLERANCE +/-10%

Labels
